



## Antimicrobial efficacy according to standard ISO/FDIS 20645

### Cleanside Oy supplied antimicrobially treated textile samples (Intimacy Curtains for healthcare)

Test method was ISO/FDIS 20645 standard (Textile fabrics – Determination of Antibacterial Activity – Agar Diffusion Plate Test).

Growth under material	Vinson rating VR	Bacteriostatic efficacy
Growth	0	No effect
Sporadius or weak growth	2	Moderate effect
No growth	4	Good effect
No growth	4+mm	Excellent effect

Test microbe: *Staphylococcus aureus* ATCC 6538 (gram-positive cocci).

### Results

Sample	
<i>Sample 1</i>	4+1 mm
<i>Sample 2</i>	4+2 mm
<i>reference</i>	0

Sample has good antibacterial efficacy against *S.aureus* according to standard used.

Helsinki 25.11.2013

Kirsi Laitinen, Laboratory Head, PhD