

Work Order	3353.2_Rev5
Setup-Code	200115-10290-2801-01



Test Report

JIS Z 2801:2012 (Mod)

Antimicrobial products – Test for antimicrobial activity and efficacy

Test Object:

AIRDAL® versus Staphylococcus aureus DSM21979 EDCC 5247 after 225 days of artificial aging



Work Order	3353.2_Rev5
Setup-Code	200115-10290-2801-0

Report on Findings

Client:

Decorative Products GmbH

Address:

Kurt-Fischer-Str. 32 22926 Ahrensburg

Germany

Work order no.:

3353.2 Rev5

Test object:

AIRDAL® versus Staphylococcus aureus DSM21979 EDCC 5247 after

225 days of artificial aging

Sample description:

Coated foil

Date of receipt of sample: 23.05.2019

Type of test:

JIS Z 2801:2012 Antimicrobial products - Test for antimicrobial activity

and efficacy

Test Germ:

Staphylococcus aureus DSM21979 EDCC 5247

Test laboratory:

QualityLabs BT GmbH

Address:

Neumeyerstrasse 46a

90411 Nuremberg, Germany

Setup-Code:

200115-10290-2801-01

Sample material:

Test plates

No. of pages in report:

7

Report on findings Place and date of preparation:

Nuremberg, 24th of April 2020

to the client:

Recipient:

Decorative Products GmbH

This revision replaces the test report from the 28th of February 2020

Laboratory Director:

Harald Gerauer, Laboratory Director QualityLabs BT GmbH

Released:

Markus Zehe, Managing Director

QualityLabs BT GmbH



Work Order	3353.2_Rev5
Setup-Code	200115-10290-2801-01

Declaration on Quality Assurance

This investigation was performed and supervised according to the standard operating procedure "SOP zu JIS Z 2801:2012 (Mod)" by QualityLabs BT GmbH. The laboratory and process are continually monitored by independent, external authorities, as well as by internal audits.

Archiving

A copy of the test report, a protocol of the measurement as well as the accompanying correspondence and business records are archived by QualityLabs BT GmbH. The retention period is at least 10 years.

Test description

Anti-bacterial activity is determined in accordance with a modified version of JIS Z 2801:2012.

During the test, a thin liquid-film containing the bacteria $(1.25 \times 10^4 \, \text{CFU} \, / \, \text{cm}^2)$ is applied directly to the test sample (Standard: 5 cm x 5 cm). To avoid desiccation a foil (Standard: 4cm x 4cm, Stomacher Bags) is applied. Immediately after inoculation, the bacteria from the reference sample are separated from the sample and the enveloping foil surfaces using ultrasound and vortex devices and the number of viable germs (CFU – colony-forming units) is determined (t_0 value). A further set of reference samples and samples given anti-microbial treatment is incubated with bacteria in a liquid-film and the enveloping foil in a damp environment at 37°C. After 24 hours, the bacteria are separated from the sample surfaces using ultrasound and vortex devices and the number of viable germs is determined (t_{24} value).



Work Order	3353.2_Rev5
Setup-Code	200115-10290-2801-01

Assessment of antimicrobial activity

A logarithmic germ reduction of \geq 3 log scales of the antimicrobial sample in comparison to the respective reference is used as assessment criterion to pass the antimicrobial test.

Germ reduktion [log scales]	Antibacterial activity	
< 3	Not sufficient antimicrobial activity	
≥ 3	Sufficient antimicrobial activity	



Work Order	3353.2_Rev5
Setup-Code	200115-10290-2801-01

References to Testconditions

Testconditions				
Sample size	25	cm ²		
Foil size	16	cm ²		
Volume Inoculum	400	μΙ		
Sample cleaning	-	-		

References to deviations, preincubations, special test conditions

The samples were stored for 225 days at 50 $^{\circ}$ C, which corresponds to an artificial aging of 4 years according to ASTM F 1980.



Work Order	3353.2_Rev5
Setup-Code	200115-10290-2801-01

Test Results

	Sample Name	Sample Code		t _o (cells/cm²)		i	₂₄ (cells/cm ²)		Reduction [%]	Log Reduction
1	Reference sample	102902805190017	4.7 x 10 ⁴	5.8 x 10 ⁴	5.8 x 10 ⁴	1.5 x 10 ⁵	1.5 x 10 ⁵	1.7 x 10 ⁵	-	Reference
2	AIRDAL [®]	102902805190018				< 1.0 x 10 ¹	< 1.0 x 10 ¹	< 1.0 x 10 ¹	> 99.99	> 4

^{*}see "Interpretation of Results", page 6

Test strain	Staphylococcus aureus DSM21979 EDCC 5247	
Initial cell count inoculum / cm²	1.25 x 10⁴	
Initials of the editor	MZ	
Measurement ended on	Jan-27-2020	



Work Order	3353.2_Rev5
Setup-Code	200115-10290-2801-01

Commen	ts on tes	st objects
--------	-----------	------------

NONE

Interpretation of the results based on the measurements

NONE

Editor: Mr. Zehe 42 Crosschecked: Mr. Mannala 67M

References

JIS Z 2801:2012 Antimicrobial products - Test for antimicrobial activity and efficacy